



SOCAR POLYMER POLYETHYLENE PRODUCT PORTFOLIO

BAKU
2019



ABOUT US

SOCAR Polymer was founded on July 16, 2013 in order to reinforce the development of the chemical industry of the country. The company's production facilities consist of the Polypropylene (PP) and High-Density Polyethylene (HDPE) plants located within the territory of the Sumgait Chemical Industrial Park (SCIP).



With 184 and 120 KTA of design production capacity, the PP and HDPE plants started operations in July 2018 and in February 2019, respectively.



OUR MISSION, VISION & GOALS

MISSION

- Polypropylene (184 KTA) and High Density Polyethylene (120 KTA) plants of SOCAR Polymer will be the first of its kind in Azerbaijan, enabling the country to grow its petrochemical industry through development of production for this segment of plastics market.

VISION

- SOCAR Polymer's vision is to be an industry leader in the region and reinforce development of chemical industry of the country
- SOCAR Polymer's vision is to be an industry leader in the region and reinforce development of chemical industry of the country
- To become competitive and create a sustainable competitive advantage businesses in the region.

STRATEGY

- Tools: Implement best in class digital systems to enable competitive advantage
- Process: Apply Internationally recognized standards and processes to become industry leader
- People: Have highly competent and strategically-aligned people to run the competitive business



SOCAR HDPE PORTFOLIO

SOCAR Polymer offers a range of HDPE/MDPE grades with a wide range of applications in the areas of flexible and rigid packaging, and industrial and consumer products.



PE FOR EXTRUSION BLOW MOLDING AND INJECTION MOLDING

Market segment	Grade name	Type of polymer	MFR, g/10 min (190°C)	Density, g/cm ³	MWD	Notes
Rigid Packaging	HD 0455 BM	HDPE	0.35 (2.16 kg)	0.955	Broad	Small EBM – Chromium
	HD 0358 BM	HDPE	0.30 (2.16 kg)	0.958	Bimodal	Small EBM – Ziegler, high swell option
	HD 0853 MO	HDPE	0.8 (2.16 kg)	0.953	Bimodal	Injection Molding – Caps & Closures
	HH 0961 MO	HDPE	8.5 (2.16 kg)	0.961	Narrow	Injection Molding – Crates & Bins
	HH 2053 MO	HDPE	20 (2.16 kg)	0.953	Narrow	Injection Molding – High flowability
Industrial Packaging	HL 1052 BM	HDPE	10 (HLMI - 21.6 kg)	0.952	Broad	Medium & Large EBM – up to 60 L
	HL 0650 BM	HDPE	6.0 (HLMI - 21.6 kg)	0.950	Broad	Very large EBM – 1500 L

Test methods:

Melt Flow Rate (MFR at 190°C/2.16, 5.0 or HLMI at 190°C/21.6 kg) according ISO1133

Density (at 23°C) according ISO1183

For Technical Data Sheet and Material Safety Data Sheet contact by e-mail to: sales@socarpolymer.az



PE FOR PIPE EXTRUSION AND FILM APPLICATION

Market segment	Grade name	Type of polymer	MFR, g/10 min (190°C)	Density, g/cm ³	MWD	Notes
Flexible Packaging	HL 0853 BF	HDPE	8.0 (HLMI - 21.6 kg)	0.953	Bimodal	Very thin blown films, for high speed lines
	HL 1050 BF	HDPE	9.5 (HLMI - 21.6 kg)	0.950	Bimodal	Very thin blown films, for high speed lines
	HL 1053 BF	HDPE	10 (HLMI -21.6 kg)	0.953	Broad	Thin blown film
Pipes / Industrial	HM 2055 EX	HDPE	2.0 (5.0 kg)	0.955	Bimodal	Extrusion coating
	HM 0949 PE80	MDPE	0.85 (5.0 kg)	0.949	Broad	Black MDPE compound - PE-80 Pipes
	HM 0359 PE100	HDPE	0.3 (5.0 kg)	0.959	Bimodal	Black HDPE compound - PE-100 Pipes
	HM 0359 PE100RC	HDPE	0.3 (5.0 kg)	0.959	Bimodal	Black HDPE compound - PE-100RC Pipes

Test methods:

Melt Flow Rate (MFR at 190°C/2.16, 5.0 or HLMI at 190°C/21.6 kg) according ISO1133

Density (at 23°C) according ISO1183

For Technical Data Sheet and Material Safety Data Sheet contact by e-mail to: sales@socarpolymer.az



DISCLAIMER

The information contained herein is to our knowledge accurate and reliable as of the date of publication. SOCAR POLYMER extend no warranties and make no representations as to the accuracy or completeness of the information contained herein, and assume no responsibility regarding the consequences of its use or for any errors. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products. Nothing herein shall constitute any warranty (express or implied, of merchantability, fitness for a particular purpose, compliance with performance indicators, conformity to samples or models, non-infringement or otherwise), nor is protection from any law or patent to be inferred. Insofar as products supplied by SOCAR POLYMER are used in conjunction with third-party materials, it is the responsibility of the customer to obtain all necessary information relating to the third-party materials and ensure that SOCAR POLYMER products, when used together with these materials, are suitable for the customer's particular purpose. No liability can be accepted in respect of the use of SOCAR POLYMER products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third-party materials.

